



SHAKUN POLYMERS PRIVATE LIMITED

SPL-S 4300- FR RoHS

FLAME RETARDANT PVC COMPOUND

Description

SPL-S 4300-FR RoHS is a Highly Flame Retardant, **UV stabilized** PVC based **RoHS** Compound for Jacketing/Sheathing applications in a wide variety of cables including **CMR** depending upon cable construction. **SPL-S 4300-FR RoHS** is formulated with a high quality resin with special plastiser, stabilizers and flame retardant chemicals.

Specifications

Cables manufactured with **SPL-S 4300-FR RoHS** according to standard technology can meet IEC 60502-1 & IS:5831 Type ST2, ST1 Specifications.

Properties

<i>Property</i>	<i>Test Method</i>	<i>Unit</i>	<i>Typical Value</i>
Density	ASTM D 792	g/cm ³	1.55
Durometer Hardness	ASTM D 2240	Shore A	91
Tensile Strength	IEC 60811-1-1	MPa	17
Elongation	IEC 60811-1-1	%	260
Variation in Tensile Properties after Heat Ageing at 100°C for 7days			
Tensile Strength	IEC 60811-1-2	%	+7
Elongation	IEC 60811-1-2	%	-5
Retention of Tensile Properties after UV-Exposure for 720 Hours			
Tensile Strength	UL 1581	%	91
Elongation		%	88
Limiting Oxygen Index	ASTM D 2863	%	43
Hot Deformation Test 80°C, 6 Hrs	IEC 60811-3-1	%	26
Thermal Stability	IEC 60811-3-2	Minutes	120

* Tensile Properties on 1mm Extruded Tape

* Data should not be used for specification work

Processing Techniques

SPL-S 4300-FR RoHS can be processed on any good extruder designed for PVC at temperatures in the range of 140°C-180°C. The screw must have a good homogenizing capacity.

Colorability

SPL-S 4300-FR RoHS is a Colorable Compound and no detrimental effects on properties in presence of masterbatch colours. We suggest drying the masterbatch before use.

Packaging

SPL-S 4300-FR RoHS is available in the form of free flowing pellets and supplied in bags of moisture resistant material with a net content of 30 Kgs. Material also available in Jumbo Bags with a net content of 900 Kgs.

2 ##**Storage & shelf life**

The product/compound should remain in

- Sealed condition
- Without exposing to direct sunlight and temperature not exceeding 45°C

Shelf life of the compound is 12 months from the date of manufacture.

Product alteration may occur due to extended period of storage.

Shakun accepts no liability of any kind in case the above mentioned storage conditions are not fulfilled.

Safety

SPL-S 4300-FR RoHS is not classified as a dangerous preparation.

The product is supplied in form of pellets of about 3 – 4 mm in size and can be readily handled with commercially available equipment. All handling and transport of the product may generate some dust and fines, which constitute a potential risk for dust explosion. Therefore, all instruments in the system should be properly grounded. Properly designed equipment and good storage will reduce the potential risk. Please, check and follow local disposal regulations!

Inhalation of any type of dust may irritate the air passages and should be avoided. For hot products: immediately immerse in or flush the affected area with large amounts of cold water to dissipate heat.

In case of adverse exposure to melting products formed at elevated temperatures, immediately remove, the affected victim from exposure.

Sweep up spilled granules and place in suitable containers for recycle or disposal. Consult an expert on disposal or recovered material and ensure conformity to local disposal regulations.

The product is intended for industrial use only. A Material Safety Datasheet is available on request. Please contact our Technical Team at SHAKUN POLYMERS PRIVATE LTD. for more details on various aspects of safety, recovery and disposal of the product.

This information is to the best of our knowledge accurate but all recommendations or suggestions are made without guarantee or legal liabilities since the conditions of use are beyond our control. The typical values given do not constitute specification for the product but represent typical analytical values.

SHAKUN POLYMERS PRIVATE LIMITED

Regd. Office : 501-504, ISCON Heights Atria-2, Gotri Road, Vadodara-390 021, India.

TEL: 00-91-265-6196500 Fax #: 00-91-265-6196565

Web Site : www.shakunpolymers.com Email : sales@shakunpolymers.com
