



SHAKUN POLYMERS PRIVATE LIMITED



SPL-ZHFR-4800D

ZERO-HALOGEN LOW SMOKE FLAME RETARDANT COMPOUND**Description**

SPL-ZHFR-4800D is a Thermoplastic, Zero Halogen, Low Smoke, Highly Flame Retardant, RoHS compliance, UV stabilized, Polyolefin based compound for separation sheath, sheathing/Jacketing of small diameter (upto 20mm) cables and Optic fiber cables.

Specifications

Cables manufactured with **SPL-ZHFR-4800D** according to standard technology meet the following industrial cable specifications.

- IEC 60332-1/IEC 60332-2/ IEC 60332-3
- DIN VDE 0207 Pt-24 Type HM2 & HM4

Properties

Property	Test Method	Unit	Typical Value
Density at 27°C	ASTM D 792	g/cm ³	1.60
Melt Index at 21.6 kg & 160°C	ASTM D 1238	g/10min	6
Hardness	ASTM D 2240	Shore D	55
Tensile Strength at Break	IEC 60811-1-1	MPa	11
Elongation at Break	IEC 60811-1-1	%	170
Variation in Tensile Properties after heat ageing (7 days at 110°C) - Tensile strength - Elongation at break	IEC 60811-1-2	%	+11 - 8
Retention of Tensile Properties after UV-Exposure for 720 Hours Tensile Strength Elongation at break	ASTM G 154	%	87 85
Limiting Oxygen Index	ASTM D 2863	% O ₂	40
Temperature Index	ASTM D 2863	° C	325
Smoke Density Rating	ASTM D 2843	%	4
Halogen Acid Gas Generation	IEC 60754-1	%	Nil
Toxicity Index	NES 713	-	1.3
Hot Pressure Test at 90°C, 4 hrs	IEC 60811-3-1	%	38
Test on gases evolved during combustion pH.	IEC 60754-2	pH	5.5
Conductivity		μs / mm	1.2

* Tensile Properties on 1mm Extruded Tape

* Data should not be used for specification work

Processing Techniques

SPL-ZHFR-4800D can be processed in a wide range of commercially available fabrication equipment. In general, it is recommended that this product be processed using low C/R screw rather than regular polyethylene screw. The recommended extrusion temperature of **SPL-ZHFR-4800D** is in the range of 130 - 170°C. Specific recommendations for processing conditions can be determined only when the application and type of equipment are known.

Predrying of compound in dehumidifying drier for 2 hours at 70°C is recommended to obtain a cable having smooth and glossy appearance.

Packaging

SPL-ZHFR-4800D is available in the form of free flowing pellets and supplied in bags of moisture resistant material with a net content of 30 Kgs. Material also available in Jumbo Boxes with a net content of 1000 Kgs.

Storage & shelf life

The product/compound should remain in

- Sealed condition
- Without exposing to direct sunlight and temperature not exceeding 45°C

Shelf life of the compound is 12 months from the date of manufacture.

Product alteration may occur due to extended period of storage.

Shakun accepts no liability of any kind in case the above mentioned storage conditions are not fulfilled.

Safety

SPL-ZHFR-4800D is not classified as a dangerous preparation.

The product is supplied in form of pellets of about 2 – 3 mm in size and can be readily handled with commercially available equipment. All handling and transport of the product may generate some dust and fines, which constitute a potential risk for dust explosion. Therefore, all instruments in the system should be properly grounded. Properly designed equipment and good storage will reduce the potential risk. Please, check and follow local disposal regulations!

Inhalation of any type of dust may irritate the air passages and should be avoided. For hot products: immediately immerse in or flush the affected area with large amounts of cold water to dissipate heat.

In case of adverse exposure to melting products formed at elevated temperatures, immediately remove, the affected victim from exposure.

Sweep up spilled granules and place in suitable containers for recycle or disposal. Consult an expert on disposal or recovered material and ensure conformity to local disposal regulations.

The product is intended for industrial use only. A Material Safety Datasheet is available on request. Please contact our Technical Team at SHAKUN POLYMERS PRIVATE LTD., for more details on various aspects of safety, recovery and disposal of the product.

This information is to the best of our knowledge accurate but all recommendations or suggestions are made without guarantee or legal liabilities since the conditions of use are beyond our control. The typical values given do not constitute specification for the product but represent typical analytical values.

SHAKUN POLYMERS PRIVATE LIMITED

Regd. Office : 501-504, ISCON Heights Atria-2, Gotri Road, Vadodara-390 021, India.

TEL: 00-91-265-6196500 Fax #: 00-91-265-6196565

Web Site : www.shakunpolymers.com Email : sales@shakunpolymers.com
