



Shakun Polymers is part of  
Alphagary, an Orbia business



Polymer  
Solutions

alphagary

15/09/2025  
Rev.02

# VINYLTEK®

## SPL-VTEK-66 RoHS

### HIGH PERFORMANCE PVC BASED TPR COMPOUND

#### DESCRIPTION

**SPL-VTEK-66 RoHS** is a High performance PVC based, RoHS & REACH compliant, TPR Compound for Jacketing/Sheathing of flexible Cables. **SPL-VTEK-66 RoHS** exhibits very good flexibility, mechanical properties and is resistant to attack by oils. It has good Abrasion Resistance Properties.

#### SPECIFICATION

**SPL-VTEK-66 RoHS** meets AS/NZS 3808 Type V-90HT specification.

**Temperature range:** -40°C to 105°C

#### PROPERTIES

Properties	Test Method	Unit	Typical Value
Density	ASTM D 792	g/cm <sup>3</sup>	1.35
Tensile Strength	IEC 60811-1-1	MPa	17
Elongation	IEC 60811-1-1	%	375
- Variation of Tensile Properties after Heat Ageing at 120°C $\pm$ 2°C for 21 days			
Tensile Strength	IEC 60811-1-2	%	+15
Elongation	IEC 60811-1-2	%	- 8
Hardness	ASTM D 2240	Shore A	80
Oil Resistance in IRM 902 Oil at 120°C for 18 Hrs., % variation in Tensile Properties	IEC 60811-2-1	%	+12
Tensile Strength			-17
Elongation			
Oil Resistance in IRM 903 Oil at 100°C for 168 Hrs., % variation in Tensile Properties	IEC 60811-2-1	%	+5
Tensile Strength			- 16
Elongation			
Thermal Stability @ 200°C	IEC 60811-3-2	Minutes	170

\* **Tensile Properties on 1mm Extruded Tape**

\* Data should not be used for specification work



Shakun Polymers is part of  
Alphagary, an Orbia business



Polymer  
Solutions

alphagary

## PROCESSING TECHNIQUES

**SPL-VTEK-66 RoHS** is an easily processable material on conventional PVC extruders. Recommended extrusion temperatures are in the range of 130°C-190°C. Specific Processing conditions can be determined only by trials on individual equipment.

## PACKAGING

**SPL-VTEK-66 RoHS** is available in the form of free flowing pellets in Raffia bags with a net content of 30 Kgs.

## STORAGE & SHELF LIFE

The product/compound should remain in

- Sealed condition
- Without exposing to direct sunlight and temperature not exceeding 45°C

Shelf life of the compound is 12 months from the date of manufacture.

Product alteration may occur due to extended period of storage.

Shakun accepts no liability of any kind in case the above-mentioned storage conditions are not fulfilled.

## SAFETY

**SPL-VTEK-66 RoHS** is not classified as a dangerous preparation.

The product is supplied in form of pellets of about 3 – 4 mm in size and can be readily handled with commercially available equipment. All handling and transport of the product may generate some dust and fines, which constitute a potential risk for dust explosion. Therefore, all instruments in the system should be properly grounded. Properly designed equipment and good storage will reduce the potential risk. Please, check and follow local disposal regulations!

Inhalation of any type of dust may irritate the air passages and should be avoided. For hot products: immediately immerse in or flush the affected area with large amounts of cold water to dissipate heat.

In case of adverse exposure to melting products formed at elevated temperatures, immediately remove, the affected victim from exposure.

Sweep up spilled granules and place in suitable containers for recycle or disposal. Consult an expert on disposal or recovered material and ensure conformity to local disposal regulations.

The product is intended for industrial use only. A Material Safety Datasheet is available on request. Please contact our Technical Team of SHAKUN POLYMERS PRIVATE LTD., for more details on various aspects of safety, recovery and disposal of the product.

This information is to the best of our knowledge accurate but all recommendations or suggestions are made without guarantee or legal liabilities since the conditions of use are beyond our control. The typical values given do not constitute specification for the product but represent typical analytical values.

## SHAKUN POLYMERS PRIVATE LIMITED

Regd. Office : 501-504, ISCON Heights Atria-2, Gotri Road, Vadodara-390 021, India.

TEL: 00-91-265-6196500



[www.shakunpolymers.com](http://www.shakunpolymers.com)



[sales@shakunpolymers.com](mailto:sales@shakunpolymers.com)